

Test report of Fly Ash- BS 3892

Sr.No.	Parameters	Unit	Result Obtained	Protocol
1	Loss on Ignition	%	0.25	BS 3892:P-1:1997
2	Silica as SiO ₂	%	51.32	BS 3892:P-1:1997
3	Alumina as Al ₂ O ₃	%	22.64	BS 3892:P-1:1997
4	Titania as TiO ₂	%	1.04	BS 3892:P-1:1997
5	Iron as Fe ₂ O ₃	%	8.87	BS 3892:P-1:1997
6	Calcium as Cao	%	5.61	BS 3892:P-1:1997
7	Magnesium as MgO	%	4.99	BS 3892:P-1:1997
8	Sodium as Na ₂ O	%	1.90	BS 3892:P-1:1997
9	Potassium as K ₂ O	%	1.28	BS 3892:P-1:1997
10	Sulphur trioxide as SO ₃	%	0.85	BS 3892:P-1:1997
11	Manganese as MnO	%	0.08	BS 3892:P-1:1997
12	Chloride as Cl	%	0.05	BS 3892:P-1:1997
13	Phosphorus as P ₂ O ₅	%	0.27	BS 3892:P-1:1997
14	Residue on 45 Micron Sieve	%	8.06	BS 3892:P-1:1997
15	Moisture	%	0.02	BS 3892:P-1:1997

Yours Truly,

**For
ROYAL MINERAL**



Irfan Jat