

Test report of Silica Sand(Foundry Grade)

Parameters	Unit	Test limits
Silica as SiO ₂	%	98.7 to 99.2
Iron as Fe ₂ O ₃	%	0.05 to 0.07
Alumina As Al ₂ O ₃	%	0.25 to 0.35
Fraction retained on 52 Mesh	%	0.2 to 0.3
Fraction retained on 120 Mesh	%	99.5 to 99.8
Fraction retained on 200 Mesh	%	0.5 to 0.10
AFS	%	65 to 70

Yours Truly,

**For
ROYAL MINERAL**



Irfan Jat