

SUPERLITE ASBESTOS FREE

Basis

Gasket material based on Aramid fibre, Glass fibre, inorganic fillers with NBR binder.

Application

Suitable for oils, fuels, lubricants, alcohols, gases, hydrocarbons, steam, water, cooling liquids, most diluted acids and alkalies for high stress conditions



90 80 3 70 60 50 40 30 1 2 20 10 175 275 325 375 Temperature (°C)

Dimensions of the standard sheets:

Standard sheet sizes:

1500 X1500 mm,1500 X2250mm, 1500 X4500 mm,1500 X1000 mm,1000X1000mm 1500 X4000 mm, 1500 X2000 mm, 1300 X3900 mm, 1270 X1270 mm, 2100 X 3000 mm, 1500 X 3000 mm.

Areas of application

- 1. This area refer, the gasket material is normally suitable subject to chemical compatibility.
- 2. This area refer, the gasket material may be suitable but a technical support is recommended.
- 3. This area refer, do not install the gasket without technical evaluation.

- Specification : ASTM
- Finish: Green / White (other Colour on Customer requirement).

Technical data

All data are typical values and refer to sheet thickness of 2.00 mm

	Test method	Specified Value	Unit
Max. Peak Temperature		-50 to 400	°C
Max. Operating Temperature		-25 to 300	°C
Max. Operating Pressure		80	Bar
Density	ASTM F 1315	1.60 - 1.90	g/cm³
Compressibility	ASTM F 36 J	5 -15.0	%
Recovery	ASTM F 36 J	≥ 45.0	%
Tensile Strength	ASTM F 152	≥ 8.0	N/mm ²
ASTM oil no.3 (5h, 150°C)	ASTM F 146		
Thickness Increase		≤ 5.0	%
Weight Increase		≤ 10.0	%
Fuel B (5h, 23°C)	ASTM F 146		
Thickness Increase	A	≤ 5.0	%
Weight Increase		≤ 12.0	%
Water (5h, 100°C)	ASTM F 146		
Thickness Increase		≤ 5.0	%
Weight Increase		≤ 5.0	%
Stress Relaxation (16h X 300°C 2.00mm)	DIN 52913	≥ 30.0	mpa

All information and recommendations given in this brochure are correct to the best of our knowledge.

However, in view of the wide variety of possible installation and operating conditions one cannot draw the final conculusion in all application cases regarding the behaviour in a gasket joint. Therefore, information can only serve as a guideline.