

SUPERLITE ASBESTOS FREE

Basis

Gasket material based on Carbon fibre, aramid fibre with NBR binder

Application

General purpose grade suitable for low pressure steam, water, oils, fuels and inert gases for low stress conditions



120100 80 80 60 40 1 20 0 50 100 150 200 250 300 350 400 450 Temperature (°C)

Dimensions of the standard sheets:

Standard sheet sizes:

1500 X1500 mm,1500 X2250mm, 1500 X4500 mm,1500 X1000 mm,1000X1000mm 1500 X4000 mm, 1500 X2000 mm, 1300 X3900 mm, 1270 X1270 mm, 2100 X 3000 mm, 1500 X 3000 mm.

Areas of application

- 1. This area refer, the gasket material is normally suitable subject to chemical compatibility.
- 2. This area refer, the gasket material may be suitable but a technical support is recommended.
- 3. This area refer, do not install the gasket without technical evaluation.

- Specification : ASTM
- Finish: Black (other Colour on Customer requirement).

Technical data

All data are typical values and refer to sheet thickness of 2.00 mm

| | Test method | Specified Value | Unit |
|--|--------------------|-----------------|-------------------|
| Max. Peak Temperature | | 440 | °C |
| Max. Operating Temperature | | 350 | °C |
| Max. Operating Pressure | | 100 | bar |
| Density | ASTM F 1315 | 1.60 - 1.90 | g/cm ³ |
| Compressibility | ASTM F 36 J | 7 - 17.0 | % |
| Recovery | ASTM F 36 J | ≥ 40.0 | % |
| Tensile Strength | ASTM F 152 | ≥ 8.0 | N/mm ² |
| ASTM oil no.3 (5h, 150°C) | ASTM F 146 | | |
| Thickness Increase | | ≤ 10.0 | % |
| Weight Increase | War and the second | ≤ 10.0 | % |
| Fuel B (5h, 23°C) | ASTM F 146 | | |
| Thickness Increase | A | ≤ 10.0 | % |
| Weight Increase | | ≤ 10.0 | % |
| Water (5h, 100°C) | ASTM F 146 | ba., | |
| Thickness Increase | | ≤ 10.0 | % |
| Weight Increase | | ≤ 10.0 | % |
| Stress Relaxation (16h X 300° C, 2.00mm) | DIN 52913 | ≥ 20.0 | mpa |

All information and recommendations given in this brochure are correct to the best of our knowledge.

However, in view of the wide variety of possible installation and operating conditions one cannot draw the final conculusion in all application cases regarding the behaviour in a gasket joint. Therefore, information can only serve as a guideline.