

TECHNICAL DATA SHEET

PRIMUS Examination Natural Pre Powdered

STERILE LATEX EXAMINATION GLOVES BEADED

PRE POWDERED

Physical Dimensions

Size	Length (mm)	Palm Width (mm)	Thickness (mm) Minimum	
	Min		Palm	Finger
X SMALL		70 ± 10		
SMALL		80 ± 10		
MEDIUM	240	95 ± 10	0.08	0.08
LARGE		111 ± 10		
X LARGE		115 ± 10		

Physical Properties

Characteristics	Before Ageing	After Ageing
Tensile Strength (Mpa) Min	14	14
Ultimate Elongation (%) Min	650	500
Stress at 500% elongation (Mpa) Max	2.8	NA
Force at Break (N) Min	9	6

Powder Content <10 mg /dm²

Formulation

Curing Agent	Sulphur
Accelerators	Zinc diethyl dithio carbamate, Zinc mercapto benzthiazole
Activators	Zinc Oxide
Antioxidants	Wingstay L (Condensation product of p-cresol & dicyclopentadiene)
Stabiliser	Potassium Hydroxide
Mould Cleaner	Nitric Acid
Coagulant	Calcium Nitrate
Donning Powder	Corn Starch (US FDA Approved)

Performance Requirements

Characteristics	Related Defects	Inspection Level	AQL
Water tightness (Final Release)	Holes	G-1 Single Sampling Plan	1.5

Primary Material	Latex
Color	Natural
Shape	Anatomic
Cuff	Beaded
If Sterilized	Ethylene Oxide
Certificates	ISO 13485 : 2003 , CE Mark
Complies to	EN 455 , ASTM 3578



Packing	Size	Product Code
1 Pair in a Paper Wallet, then to a paper pouch		
50 Pouches (Pairs) in 1 Inner Box	SMALL	202112S/S
8 Inner Boxes (400 Pairs in 1 Master Shipper Carton)	MEDIUM	202112M/S
Pouch Size : 13 x 21 Cm Peel Open Type	LARGE	202112L/S

Manufactured By : PRIMUS Gloves Pvt Limited, Plot No 14-A, Cochin Special Economic Zone, Kakkannad, Cochin 682037, Kerala, INDIA
 Tel : + 91 484 2413063, 2413076 ; Fax : + 91 484 2413089
 Email: marketing@primusgloves.com; primusgloves@gmail.com
 Web : www.primusgloves.com



Issue date : 01.09.2010