

Dholpur Stone adhesive

Description:

Cetfix DSA is polymer modified white cement based powder needs to be mixed with water for installation large vitrified tile and natural stone on internal and external cladding..

Advantages:

- Excellent adhesion, low shrinkage
- Accommodate physical & thermal movements
- Ready to use, No curing required
- Floor can be used after 24 hours

Area of application:

- Dholpur stone,
- Interior & exterior stone cladding.

Direction of use:

Surface Preparation:

- The surface should be sound and thoroughly cleaned.

Mixing:

- Mix 3 parts cetfix DSA and 1 part of CETCRETE AR by volume to stiff consistency.
- Leave for 5 minute and remix.
- Use within 30 minutes.

Application;

- Spread the adhesive to a required bed thickness and comb with notched trowel.
- Then start placing the Dholpur tiles on the surface within 15 to 20 min.
- Press the tiles firmly into position with a slight twisting action.
- Clean off surplus adhesive from the Dholpur tile face and between joints.
- Joint filler cetfix TG apply after 24 hours

Coverage:

2 to 2.5 sqm. per 20 kg bag at 6 mm bedding thickness.

Packing:

Supplied in 20 kg bag.

Disclaimer: The product information & application details given by the company & its agents have been provided only as a general guideline for usage. No guarantee / warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products



CETCON Building Technologies Pvt. Ltd.

13, Milan Estate, Opp. Shah Foils Ltd, Santej- Khatraj Road, At: Santej,
Dist: Gandhinagar - 382721, Gujarat, India.

Mobile : +91-97279 00055, +91-97129 00055, Fax : +91-79-2759 1055

Email : contact@cetconindia.com, Website <http://cetconindia.com>

Reg. Office: C-301, Akash Residency, GST Crossing, New Ranip,
Ahmedabad – 382470.

CIN : U24132GJ2013PTCO73641

