

Polymer based modified cementitious tile joint grout.

Description:

Cetfix TG is polymer modified cement based tile joint colour grout for filling joints of ceramics tiles, Vitrified tiles, marble, Natural stone, terrazzo, granite and glass mosaic tiles.

Advantages:

- Waterproof
- Crack-proof
- Peel-proof
- Easy to use and clean
- Uniform colour, ready to use

Area of application:

Filling tiling joints in

- Bathrooms
- Kitchen Wash area.
- Swimming pools

Direction of use:

Mixing:

- The tiling joint should be made clean, dry and free from contamination.
- Mix 3 to 3.5 parts cetfix TG and 1 part of water by volume to smooth consistency.
- Leave for 5 minute and remix, use within 60 minutes.

Application:

- Apply the paste to the joints with a sponge / squeeze trowel.
- Remove surplus CETFIX TG with a damp sponge
- Allow 24 hours for the filling to dry. Then polish the tile with clean, dry cloth.
- Joint filler cetfix TG should be used after 24 hours Tiles fixing.

Sealer coat:

- For better protection and dust prevent can be used sealer coat CETCOAT MC 1 part and 1 part water mix and apply on 2 coat on to surface of grout / joint filler.
- Sealer coat CETCOAT MC should be used after 24 hours of filling of joint grout.
- Clean off surplus from the tile face and between joints.



CETFIX TG

2517

Colour:

White, Off White, Light Ivory, Ivory, Dark Ivory, Light Grey, Dark Grey and Smoke Grey.

Coverage:

Depends on the tile and width of the joint, for 2mm deep joints coverage is given below for just indicative and coverage can vary as per the site conditions and type of tiles.

Size of Tiles (inch x inch)	Tile Thickness (mm)	Consumption per kg/per sqm. (For 2 mm joint)
12 x 12	10	0.30
16 x 16	10	0.26
18 x 18	12	0.25
24 x 24	12	0.22
36 x 36	15	0.16

Packing:

Supplied in 1 kg.

Disclaimer: The product information & application details given by the company & its agents have been provided only as a general guideline for usage. No guarantee / warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products



CETCON Building Technologies Pvt. Ltd.

13, Milan Estate, Opp. Shah Foils Ltd, Santej- Khatraj Road, At: Santej,
Dist: Gandhinagar - 382721, Gujarat, India.

Mobile : +91-97279 00055, +91-97129 00055, Fax : +91-79-2759 1055

Email : contact@cetconindia.com, Website <http://cetconindia.com>

Reg. Office: C-301, Akash Residency, GST Crossing, New Ranip,
Ahmedabad – 382470.

CIN : U24132GJ2013PTCO73641

